

LOCTITE ABLESTIK 6202CB

August 2012

PRODUCT DESCRIPTION

LOCTITE ABLESTIK 6202CB provides the following product characteristics:

Technology	Proprietary Hybrid Chemistry
Appearance	Yellow
Filler Type	Silica and Rubber
Cure	Heat cure
Product Benefits	<ul style="list-style-type: none"> • Stencil printing • Low moisture uptake • Low flow (<150µm) • Low warpage • Long work life • Low modulus
Application	Die attach
Substrates	Laminate
Typical Package Application	Chip scale packages and Stencil printing

LOCTITE ABLESTIK 6202CB B-stageable adhesive is ideal for chip scale packages where tolerance and bleed need to be minimized. This low modulus adhesive is recommended for large die sizes.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Thixotropic Index (0.5/5 rpm)	2.6
Viscosity, Brookfield CP51, 25 °C, mPa·s (cP):	
Speed 5 rpm	30,000
Work Life @ 25°C, days	14
Shelf Life (from date of manufacture):	
@ -20°C, days	183
@ -40°C, days	365
Flash Point - See SDS	

TYPICAL PROCESS DATA

Recommended B-Stage Condition

90 minutes @ 125°C

Pre-Dry Prior to Die Attach

5 minutes @ 125°C

Recommended when there is a significant amount of time (i.e., 4 hours or more) between B-stage and die attach.

Chip Attach

Die Temperature, °C	130 to 160
Substrate Temperature, °C	25 to 50
Force, kg-f	2 to 6
Time, second	1

TYPICAL CURING PERFORMANCE

Cure Schedule

30 minute ramp to 100°C; 30 minutes @ 100°C + 30 minute ramp from 100°C to 175°C; 60 minutes @ 175°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Coefficient of Thermal Expansion, :		
Below Tg, ppm/°C		70
Above Tg, ppm/°C		350
Glass Transition Temperature (Tg) by TMA, °C		40
Tensile Modulus, DMTA :		
@ 25 °C	N/mm ² (psi)	500 (72,500)
@ 150 °C	N/mm ² (psi)	5 (725)
@ 250 °C	N/mm ² (psi)	6 (812)

Extractable Ionic Content, :

Chloride (Cl-)	<25
Sodium (Na+)	<20
Potassium (K+)	<20

Water Extract Conductivity, µmhos/cm	120
--------------------------------------	-----

Moisture Absorption @ Saturation, wt.% @ 1.03 85°C/85%RH	
--	--

Density before B-Stage, g/cc	1.10
------------------------------	------

Density after B-Stage, g/cc	1.15
-----------------------------	------

TYPICAL PERFORMANCE OF CURED MATERIAL

Miscellaneous

Die Shear Strength :

2 X 2 mm , kg-f,

Substrate	@25°C	@245°C
Si die to Ceramic	10.4	1.1

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

THAWING:

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. DO NOT open the container before contents reach 25°C temperature. Any moisture that collects on the thawed container should be removed prior to opening the container.
4. DO NOT re-freeze. Once thawed to 25°C, the adhesive should not be re-frozen.

DIRECTIONS FOR USE

1. Apply enough adhesive to the stencil to ensure complete filling of the stencil with a 15 to 20 mm diameter bead. Typically, this requires 20 to 50 cc of adhesive, depending on the stencil size. For two-direction printing, double beading is recommended.

- Unused adhesive may be re-frozen, provided the total time at ambient temperature does not exceed the recommended work life.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: -40 °C. Storage below minus (-)40 °C or greater than minus (-)40 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$
 $\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$
 $\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$
 $\text{mPa} \cdot \text{s} = \text{cP}$

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 2