



# LOCTITE® EDAG 479SS

November 2024

PRODUCT DESCRIPTION

LOCTITE® EDAG 479SS provides the following product characteristics:

Technology	Thermoplastic
Appearance	Gray paste
Filler type	Silver
Product benefits	<ul style="list-style-type: none"><li>• Good conductivity</li><li>• Low temperature drying</li><li>• Excellent abrasion resistance and hardness</li><li>• Excellent creasability</li><li>• Excellent fine line printing</li><li>• Extended screen residence time</li><li>• Superior adhesion to polyester film</li><li>• Screen printable</li></ul>
Operating temperature, °C	max 120°C
Cure	Heat drying
Application	Conductive ink
Typical assembly applications	Membrane switches and Fflexible circuitry display devices
Key substrates	PET, PI, PEN, paper, copper, ITO, glass

LOCTITE® EDAG 479SS is a halogen-free, conductive silver ink with good flexibility. The resistance level of LOCTITE® EDAG 479SS typically lies around 18 mOhm/sq/25µm. It can be dried at low temperature, down to 80°C. LOCTITE® EDAG 479SS is compatible with EDAG dielectric and carbon inks. This ink can further be blended with the carbon ink LOCTITE® EDAG 965SS to adjust resistance levels and make the material more economical. Thanks to good thermal and chemical stability, this product is compatible with high operating temperature, has good adhesion to many substrates, and is compatible with a large range of electrically conductive adhesives for component attach or solderable with low melting Sn42Bi58 solder. LOCTITE® EDAG 479SS is suitable for screen printing and often used to create flexible circuits, keyboards, membrane switches, medical electrodes or biosensors.

TYPICAL PROPERTIES OF UNDRIED MATERIAL

Solid content, (wt%)	75
Density, kg/l	2.56
Viscosity, Brookfield - RVT, CP 51, 25°C, mPa·s (cP)	12,000
Speed 20 rpm	
Theoretical coverage, @ 10µm dry coating thickness, m²/kg	15
Shelf life @ 2 to 8°C, (from date of manufacture), days	365
Flash point, Tag Closed Cup Flash Tester, °C	110

TYPICAL SCREEN PRINTING PROCESS

Recommended thickness	
Dry film thickness, µm	4 to 12
Emulsion thickness	
Solvent resistant emulsion, µm	20 to 40
Recommended screen type	
Monofilament polyester screen, mesh/inch	157 to 280
Stainless steel screen, mesh/inch	165 to 325
Recommended squeegee	
Polyurethane or other solvent resistant material	
Polyester screen, durometer	60 to 70
Stainless steel screen, durometer	70 to 80

TYPICAL DRYING CYCLE

Recommended drying cycle
15 minutes @ 120°C

LOCTITE® EDAG 479SS can be dried immediately after printing at temperatures 80 to 140°C. The higher the temperature, the lower the sheet resistance and the better the mechanical properties.

For high speed production jet drying, infra red drying and drying in high speed reel-to-reel equipment can be used successfully.

The above drying profile is a guideline recommendation. Conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.



<b>Percent volatiles</b>	
VOC, g/l	653
Higher temperatures and longer durations improve conductivity and film properties.	
<b>TYPICAL PROPERTIES OF THE DRIED MATERIAL</b>	
<b>Physical properties</b>	
Pencil hardness,	2H
<b>Electrical properties</b>	
Sheet resistance, 4-point probe, Ohm/sq/25µm after 45s at 90°C followed by 45s at 120°C	0.018

**Conversions**  
(°C x 1.8) + 32 = °F  
kV/mm x 25.4 = V/mil  
mm / 25.4 = inches  
µm / 25.4 = mil  
N x 0.225 = lb  
N/mm x 5.71 = lb/in  
N/mm² x 145 = psi  
MPa x 145 = psi  
N·m x 8.851 = lb·in  
N·m x 0.738 = lb·ft  
N·mm x 0.142 = oz·in  
mPa·s = cP

**Disclaimer**  
The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**GENERAL INFORMATION**  
Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

**DIRECTIONS FOR USE**

**Surface preparation**

- Clean surface thoroughly prior to application.

**Mixing/Dilution**

- Mix thoroughly before use to ensure the entire ink volume is homogenous. A slow speed propeller may be utilized to mix until product is uniform.
- Should dilution be necessary, use 2-(2-Ethoxyethoxy)ethyl acetate (CAS: 112-15-2). Henkel recommends a maximum of 10 wt%. This should be accomplished by adding solvent at 0.5 wt% intervals until desired viscosity and printability is achieved.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**Clean up**  
To clean screen and equipment, use a 25% Carbitol acetate 75% Methyllethylketone (MEK) blend.

**STORAGE**  
Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

- Do not expose to direct sunlight.
- Do not freeze.
- Keep product container tightly closed when not in use.
- Store in cool, dry, good ventilated rooms.

**Optimal storage: 2 to 8°C**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

**Not for product specifications**



**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### **Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2